


**INTERNATIONAL FASTENERS, INC.** 



MIAMIDADE

COUNTY NOA No: 22-0302.0

## SPEC DATA SUBMITTAL SHEET

## Dagger-Con<sup>™</sup> Concrete Screws · Phillips Flat · Dagger-Guard Coating<sup>™</sup>

Size	TPI	Ctn Qty	Daggerz ™ Part Number	Drive Thread		Drill Bit Size	Usable Drill Length		
3/16 x 2-1/4	16	2,500	CONCTF0316214	#3	Hi Low	5/32 x 4-1/2	2-1/4"		
3/16 x 2-3/4	16	1,500	CONCTF0316234	#3	Hi Low	5/32 x 4-1/2	2-1/4"		
3/16 x 3-1/4	16	1,500	CONCTF0316314	#3	Hi Low	5/32 x 5-1/2	3-1/4"		
3/16 x 3-3/4	16	1,000	CONCTF0316334	#3	Hi Low	5/32 x 5-1/2	3-1/4"		
material:	C1022 LOW CARBON STEEL, CORE HARDNESS: HRC32-40								
finish:	. Dagger-Guard Coating™ is a three layer, multi step dip/spin bake process which provides 1000 hour salt spray corrosion resistance, offered in WHITE or BRONZE								
application:	wood or metal to un-cracked concrete, hollow block CMU, and grouted hollow block CMU								
installation:	Drill the hole using a standard carbide drill bit with the proper diameter (3/16" anchor = 5/32" bit). Do not use a Hammer Drill. Concrete and grouted CMU - drill the hole 1/4" deeper than recommended embedment. Hollow CMU - drill the hole through the full thickness of the face shell. Drive until fully seated, do not over-torque the anchor.								

Meets or exceeds the following specifications:

	Expiration Date: 11/24/2026 MSG 5-34EL
ASTM A510	Specification for General Requirements for Wire Rods and Coarse Round Wire, Carbon Steel (Minimum grade 1018)
ASTM B117	Practice for Operating Salt Spray (Fog) Apparatus
ASTM G85	Standard Practice for Modified Salt Spray (Fog) Testing, Annex 5 Dilute Electrolyte Cyclic Fog Dry Test
ASTM E488	Strength of Anchors in Concrete Elements

	Anchor	Drill Bit	Substrate	H <sub>nom</sub>	Min.	Min.	PSI	Allowable Load (lbf)				
Diameter	Diameter	Substrate	(in.)	Spacing (in.)	Edge (in.)	P31	Tension	Shear		¥	A=Fixture being	
	3/16"	5/32"	Concrete	1-3/4"	1"	1-1/2"	2600	310	225	· · · · · ·		attached
			Ungrouted CMU	1-1/4"	1-1/8"	1-1/2"	2250	75	135			B=embedment
				1-3/4"	3"	1-1/4"	2500	190	175		Ļ	
		Grouted CMU	1-3/4"	3"	2-1/2"	2500	205	175			C=1/4" minimum	
												$B \perp C = Depth of hole$

B+C = Depth of hole

drilled

These figures are offered only as a guide and are not guaranteed in any way by International Fasteners, Inc. Appropriate safety factors should be applied to these values for specific purposes. All International Fasteners, Inc. Fasteners are manufactured to IFI's Performance Specifications and Print Drawings.

CONCTF.21